

PRODUCT DATA SHEET FOR INDUSTRIAL INSULATION

Product Name	PAROC Pro Slab 50
Manufacturer	Paroc Group Oy
Certification number	6V126
Certification body	DIN CERTCO
Designation Code	MW EN 14303-T3-ST(+)-350-WS1-CL10
Labeling	VDI-mark
Form of supply	Board
European Standard	DIN EN 14303:2013-04
Thermal Conductivity (W/mK)	
Maximum service temperature	350
Minimum service temperature	
Thickness Range (mm)	040-140
Reaction to Fire (Euroclass)	A1
Temperature 1	50
Thermal conductivity 1	0.042
Temperature 2	100
Thermal conductivity 2	0.054
Temperature 3	200
Thermal conductivity 3	0.085
Temperature 4	300
Thermal conductivity 4	0.132
Temperature 5	
Thermal conductivity 5	
Temperature 6	
Thermal conductivity 6	
Temperature 7	
Thermal conductivity 7	
Temperature 8	
Thermal conductivity 8	
Temperature 9	
Thermal conductivity 9	
Temperature 10	
Thermal conductivity 10	
Air-flow resistance	
Water vapor diffusion resistance	
Content of water-soluble chloride ions	< 10 ppm
Water absorption	<1